

König Rex Lith Transparent 151 000

Uses

- For the repair of plain surfaces subject to severe use, e.g. wood, plastics, metal, marble, stone, polyester (not to be used on polyethylene, polypropylene, teflon).
- Can be used for damages to corners and edges.
- To restore missing parts, to fill deep holes, scratches and pressure marks.
- With exterior use it is necessary to varnish.

Characteristics

- Fast hardening 2-component filler based on polyester resin/peroxide.
- Transparent.
- Processing time: approx. 5 minutes depending on hardener volume and ambient temperature.
- Little shrinkage (1-2%).
- All kinds of Rex Lith can be intermixed.
- Perfect hardness and hard-wearing properties.
- Easy to treat after curing (sanding, sawing, planing, milling).
- Can be varnished with both 1- and 2-component systems.
- Can be polished.
- Can be dyed with König touch-up products (Colour Touch-Up 240/Touch-Up Dye 220).

Application

Addition of hardener 1,5-2,5%. For dose examples see instructions for use.

Note: Overdose causes: discolouration/yellowing, creation of cracks, a too high temperature, trouble after lacquering. Processing temperature: 15-25°C. When dyeing with Colour Touch-Up 240/Touch-Up Dye 220 (5 drops maximum per 1 cm Rex Lith) hardening time may be prolonged.

Important: Always add dye prior to hardener. Homogenize both components on a non-soaking substrate (e.g. Mixing Palette 609) for approx. 1 minute. Fill damage area rapidly and avoid inclusions of air. After approx. 20-30 minutes hardening time projectings can be stripped of and surface levelled. Sticky residues to be removed with Liquid Sandpaper 711. After approx. 30 minutes touch-up work to a repair possible. A complete lacquering as a new coating only possible after 24 hours (fine intermediate sanding!).

Specifications

- Temperature resistance:** up to 110°C.
Mechanical stability: very good.
Hardening period: 20-30 minutes (dependent on temperature)
Can be lacquered over: with every König lacquer. good up to very good.
Adhesion:
Lightfastness/ weather resistance: limited.
Shelf life: 1 year (stored cool, in original unopened container)

Safety Precautions

- Flammable.
- Contains styrol.
- In case of contact with eyes rinse immediately with plenty of water and seek medical advice.
- Use only in well ventilated areas.
- Keep out of reach of children.

Extract of wordings of the law. For further information please see label and Material Safety Data Sheet.

Disposal


- In their present form Rex Lith and its Hardener are defined as special waste.
- European Waste Code 080402 – *waste adhesives and sealants free of halogenated solvents.*
- For additional information, consult the Material Safety Data Sheet for this product or ask your local waste industry office.

Packaging

120 g package + accessories
750 g can + 2 x 25 g hardener

*Further information and Material Safety Data Sheet on the internet at
www.heinrich-koenig.de*

Although reasonable care has been taken in the preparation of this document, we extend no warranties and make no representations as to the accuracy or completeness of the information contained herein, and assume no responsibility regarding the suitability of this information for the user's intended purposes or for the consequences of its use. Each individual should make a determination as to the suitability of the information for his or her particular purpose(s).



Heinrich König & Co. KG

An der Rosenhelle 5 • D-61138 Niederdorfelden
Phone: 0 61 01 - 53 60 0 • Fax: 0 61 01 - 53 60 11
E-mail: info@heinrich-koenig.de

Issue 15/03